

Comparison table of the ZEDEX® materials

Properties		Symbol / Unit	Standard	ZEDEX® basic types												ZEDEX® families														
Material code	colour			A1F	A1T	A3A	A3H	A3L	A3F	A3B	A4A	A4T	A5D	A31	A5M	A66	A5L	A7A	A8T	A9T	A05									
density	kg/dm ³	ISO 1183	1.35	black	1.2	1.49	1.30	1.33	1.34	1.48	1.33	1.42	1.51	1.67	1.47	1.30	1.44	1.36	1.44	1.53										
compressive modulus elastic limit	Ec	DIN EN ISO 604	3150	390	334	4570	4270	3700	2540	2850	5454	4700	6300	3500	2600	3500	1748	1490	1150	1411	4950									
compressive stress at yield	σ_{el}	MPa	n.v.	42	20	14	86	120	119	76	122	123	111	100	71	56	70	50,4	16	11	96									
compressive strength	σ_Y	MPa	DIN EN ISO 604	n.v.	n.v.	n.v.	n.v.	n.v.	145	103	146	n.v.	142	135	109	n.v.	n.v.	n.v.	n.v.	n.v.	115	101								
compressive stress at 3,5% strain	$\sigma_{3,5\%}$	MPa	DIN EN ISO 604	30	15	6	97	32	145	80	36	95	135	129	29	52	46	40,5	16	19	59	83								
compressive strength (0,01 h)	σ_M	MPa	DIN EN ISO 604	30	15	6	97	32	145	80	36	95	135	129	29	52	46	40,5	16	19	59	83								
compressive strength (100 h)	σ_m	MPa	DIN EN ISO 604	60	22	15	92	120	127	81	130	131	119	108	76	59	75	54	15	10	102	108								
compressive strength (10000 h)	σ_{M0}	MPa	DIN EN ISO 604	30	8,5	5,5	45	58	43	35	40	60	54	70	25	22	30	19	10	0,8	48	61								
compressive stress at break	σ_B	MPa	DIN EN ISO 604	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	112	147								
elastic compression limit	ε_{el}	%	DIN EN ISO 604	6	6,2	7,1	3,1	8,8	1,7	3,3	8,8	4,8	1,8	2,2	6,5	3,8	5	4,5	3,5	1,4	6	4,4								
nominal compressive yield strain	ε_{cv}	%	DIN EN ISO 604	n.v.	n.v.	n.v.	n.v.	28	n.v.	n.v.	3,2	2,5	5,4	12,5	n.v.	2,7	5,2	31	n.v.	7,2	n.v.	9,9	n.v.							
nominal compressive strain at compressive strength	ε_{cm}	%	DIN EN ISO 604	n.v.	n.v.	n.v.	n.v.	6,9	n.v.	n.v.	5,4	n.v.	n.v.	n.v.	n.v.	5,2	31	11	30	n.v.	n.v.	9,9	10,9							
nominal compressive strain at break	ε_{cb}	%	DIN EN ISO 527	2900	310	200	4854	3600	3500	4400	7800	3368	5499	3500	3340	3940	1500	800	850	3100	2480									
modulus in tension (tensile modulus) elastic limit	E_t	MPa	DIN EN ISO 527	65	5	4	53	81	74	76	78	64	71	42,4	47	31,8	50,6	38	9,8	6,8	35,8	61								
tensile stress at yield	σ_{el}	MPa	DIN EN ISO 527	78	19	14	-	110	-	92	113	120	101	-	-	-	-	-	12,7	-	-	-								
tensile strength	σ_M	MPa	DIN EN ISO 527	78	38	37	67	110	117	92	113	142	101	71	50	32	79	50	12,7	12	46	93,1								
tensile stress at break	σ_B	MPa	DIN EN ISO 527	70	35	30	65	84	117	90	98	2,7	82	71	50	32	79	50	10,8	12	45	93,1								
elastic yield point	ε_{el}	%	DIN EN ISO 527	1,6	1,5	2	-	4,2	5	1,5	1,3	-	1,5	1,8	1,3	0,7	2,1	3,4	1,3	4,2	2,1	2,4								
yield strain	ε_y	%	DIN EN ISO 527	4	16	20	1,1	7	-	6,9	5	-	5,5	-	-	-	-	-	2,3	-	-	-								
elongation at maximum force	ε_M	%	DIN EN ISO 527	6	>300	3	7	10,1	6,9	5	3,9	5,5	4,5	4,5	2,2	5	19,9	2,3	192	3,1	6,8									
tennis elongation at break	ε_B	%	DIN EN ISO 527	9,5	>300	5,3	126	10,1	23,9	4,5	4,5	25	4,5	4,5	2,2	5	19,9	9,2	192	3,1	6,8									
modulus in flexure	E_f	MPa	DIN EN ISO 527	3300	400	350	3955	4000	3900	2937	7000	2900	5545	3000	4030	4356	2320	1170	1190	3320	8830									
outer fiber stress at 3,5% outer fiber strain	$\sigma_{13,5}$	MPa	DIN EN ISO 117	96	12	11	103	126	117,5	110	119	150	89	129	74	x	114	63	19	15	103	177								
flexural strength	σ_M	MPa	DIN EN ISO 178	178	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	182								
flexural stress at break	σ_B	MPa	DIN EN ISO 178	6,1	8	9	4,5	6,3	6,2	5,7	6,6	-	7,3	4,8	4,9	1,6	3,7	5,6	4,2	3,3	2,2	4,3								
elongation at flexural yield stress	ε_M	%	DIN EN ISO 178	1	internal Standard	52	9	7	42	60	70	56	65	105	33	59	40	19	41	6	7	4	35	55						
flexural elongation at break	ε_B	%	DIN EN ISO 178	2000	625	400	2900	3430	3040	2500	2780	4560	4015	5260	1900	1760	2180	1300	60	61	3200	4320								
creep modulus at 1% deformation after 1000h stress at 1% deformation after 1000h	E	N/mm ²	DIN 53444	22	6,3	4	33	43	32	26	29	44	40	51	19	16	22	14	0,8	0,6	35	44								
creep resistance	σ_1	N/mm ²	DIN 53444	relative value	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2							
Shore A hardness H358/30 [H]	H		DIN 2039	136	(35)	153	174	175	190	231	159	146	134	116	157	107	(36)	110	160											
Shore D hardness	T _m		DIN 53505	84	64	56	885	81	86	87	88	85	90	83	>100	>100	>100	>100	>100	>100	>100	>100	>100	>100	>100	>100	>100	>100	>100	>100
impact strength Charpy notched loss tangent (1Hz)	T _g		EN ISO 179/1e	54	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	k.Br.	23	k.Br.	30	28	8,9	13	5,5	23,50	123	113	24,7	15,6					
fatigue strength at 20°C, 10° stress cycles 1 Hz continuous operating temperature (long term)	R _{Ti}	°C	UL 746B	110	75	75	130	250	250	250	180	190	240	240	170	170	240	240	240	240	240	280								
short term operating temperature (3 h)		°C	internal Standard	140	80	80	150	260	260	260	260	260	260	260	260	260	260	260	260	260	260	320								
maximum temperature for pressed bushings		°C	internal Standard	65	50	65	100	140	115	140	140	150	150	90	95	90	95	90	70	40	70	250	250							
melting point	T _m		DSC	250	212	207	250	340	340	340	340	340	340	320	320	320	320	320	320	320	320	320	320							
glass transition temperature	T _g		DSC	78	-60	-64	80	146	146	146	146	146	146	211	211	211	211	211	90	90	-20	-20	-20							
coefficient of thermal expansion up to 100°C	α	10 ⁻⁵ K ⁻¹	ISO E 830	8	14	16,7	7,1	5,1	4,7	6,2	5,8	3,6	4,0	2,3	6	3,8	6	12	14,4	4	2,7									
heat distortion temperature HDT/A, 1,8 MPa	HDT(A)	°C	ISO E 831	12	16,3	16,2	10,7	5,9	6,5	5,8	3,8	2,5	9	4,6	5,0	6,7	16	19,2	4,7	2,9										
thermal conductivity	λ	W/(m·K)	DIN 52612	0,24	-	0,28	-	0,24	0,25	-	0,24	0,24	0,25	-	-	-	-	-	0,24	0,24	-	-	-							
specific heat capacity	c _p	J/K·(kg·K)	DSC	1,06	1,23	1,15	1,35	1,09	1,05	1,09	1,06	1,06	1,06	1,06	0,87	0,89	0,84	1,81	0,84	0,93	1,18	0,080								
fire behaviour (3,2mm) UL94			UL 94 HB	94HB	94HB	V-0	V-0	V-0	V-0	V-0	V-0	V-0	V-0	V-0	V-0	V-0	V-0	V-0												
oxygen index	%	LOI	DIN EN ISO 4589	24	-	-	35	16	-	-	43	47	-	-	-	-	-	-	-	-	-	95	75	52	-	-	-	-	-	-

Comparison table of the ZEDEX® materials

All the tests are been made with a standard conditioning atmosphere of 23°C (at the moment no other temperature is available). The specified values are established from average values of several tests and they correspond to our today's knowledge. They are only to be used as information about our products and as help for the material selection. With these values, we do not ensure specific properties, or the suitability for certain application, therefore we do not assume any legal responsibility for an improper usage. The used test pieces have been machined from extruded semi-finished material. Since the plastics' properties depend on the manufacturing process (extrusion, injection molding), on the dimensions of the semi finished material and on the degree of crystallinity, the actual properties of a specific product may slightly deviate from the tested ones. For information about divergent properties do not hesitate to contact us. On request we advise you regarding the most appropriate component design and the definition of material specificities in pharmaceutical applications, medical devices or other end uses.

Updated: September 2010